



Designation: D4035 – 22

## Standard Performance Specification for Knitted Necktie and Scarf Fabrics<sup>1</sup>

This standard is issued under the fixed designation D4035; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This performance specification covers knitted necktie and scarf fabrics composed of any textile fiber or mixture of textile fibers.

1.2 These requirements apply to the length and width directions for those properties where fabric direction is pertinent.

1.3 The following precautionary statement pertains only to the test methods portion, Section 7, of this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

D123 Terminology Relating to Textiles

D2594 Test Method for Stretch Properties of Knitted Fabrics Having Low Power

D2724 Test Method for Bond Strength of Bonded, Fused, and Laminated Apparel Fabrics

D2905 Practice for Statements on Number of Specimens for Textiles (Withdrawn 2008)<sup>3</sup>

D3786 Test Method for Bursting Strength of Textile Fabrics—Diaphragm Bursting Strength Tester Method

D3787 Test Method for Bursting Strength of Textiles—Constant-Rate-of-Traverse (CRT) Ball Burst Test

D7022 Terminology Relating to Apparel<sup>3</sup>

2.2 *AATCC Methods:*<sup>4</sup>

TM8 Colorfastness to Crocking: Crockmeter Method

TM15 Colorfastness to Perspiration

TM16.3 Colorfastness to Light

TM23 Colorfastness to Burnt Gas Fumes

TM61 Colorfastness to Laundering: Accelerated

TM96 Dimensional Changes in Commercial Laundering of Woven and Knitted Fabrics Except Wool

TM116 Colorfastness to Crocking: Rotary Vertical Crockmeter Method

TM124 Smoothness Appearance of Fabrics After Repeated Home Laundering

TM132 Colorfastness to Drycleaning

TM135 Dimensional Changes of Fabrics

TM172 Colorfastness to Powdered Non-Chlorine Bleach in Home Laundering

TM188 Colorfastness to Sodium Hypochlorite Bleach in Home Laundering

EP1 Gray Scale for Color Change

EP2 Gray Scale for Staining

EP8 AATCC 9-Step Chromatic Transference Scale

2.3 *Federal Standard:*<sup>5</sup>

16 CFR 1610—Standard for Flammability of Clothing Textiles

NOTE 1—Reference to test methods in this specification give only the permanent part of the designation of ASTM, AATCC, or other test methods. The current editions of each test method cited shall prevail.

### 3. Terminology

3.1 For all terminology related to D13.61, Apparel, see Terminology D7022.

3.1.1 The following terms are relevant to this standard: necktie, scarf, *in apparel*.

3.2 For definitions of all other textile terms, see Terminology D123.

<sup>1</sup> This performance specification is under the jurisdiction of ASTM Committee D13 on Textiles and is the direct responsibility of Subcommittee D13.61 on Apparel.

Current edition approved Nov. 1, 2022. Published December 2022. Originally approved in 1981. Last previous edition approved in 2014 as D4035 – 14. DOI: 10.1520/D4035-22.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

<sup>4</sup> Available from American Association of Textile Chemists and Colorists (AATCC), P.O. Box 12215, Research Triangle Park, NC 27709, <http://www.aatcc.org>.

<sup>5</sup> Available from Superintendent of Documents, Government Printing Office, Washington, DC 20402.

3.3 For terms relating to chemical or colorfastness testing, refer to specific AATCC methods.

#### 4. Specification Requirements

4.1 The properties of fabrics for neckties and scarfs shall conform to the specification requirements in [Table 1](#).

#### 5. Significance and Use

5.1 Upon mutual agreement between the purchaser and the seller, fabrics intended for this end use should meet all of the requirements listed in [Table 1](#) of this specification.

5.2 It is recognized that for purposes of fashion or aesthetics the ultimate consumer of articles made from these fabrics may find acceptable fabrics that do not conform to all of the requirements in [Table 1](#). Therefore, one or more of the requirements listed in [Table 1](#) may be modified by mutual agreement between the purchaser and the seller.

5.2.1 In such cases, any references to the specification shall specify that: “This fabric meets ASTM Specification D4035 except for the following characteristic(s).”

5.3 Where no prepurchase agreement has been reached between the purchaser and the seller, and in case of controversy, the requirements listed in [Table 1](#) are intended to be used as a guide only. As noted in [5.2](#), ultimate consumer

demands dictate varying performance parameters for any particular style of fabric.

5.4 The significance and use of particular properties and test methods are discussed in the appropriate sections of the specified test methods.

#### 6. Sampling

6.1 Tests shall be performed on the fabric as it will reach the consumer. Any “partially finished” or “post-finished” fabrics should first be processed in accordance with the fabric manufacturer’s instructions.

6.2 Unless otherwise agreed upon, as when specified in an applicable material specification, take the number of specimens directed in each of the applicable test methods.

6.2.1 If there has been no prior agreement and the test method does not specify the number of specimens, use the procedures in [Practice D2905](#) to determine the number of specimens, such that the user may expect at the 95 % probability level that the test result is no more than 5 % of the average above or below the lot average (that is, the average that would be obtained by applying this method to the entire lot) when using a reliable estimate of variability of individual observations on similar materials in the user’s laboratory under conditions of single-operator precision.

#### 7. Test Methods (see [Note 1](#))

7.1 *Bursting Strength*—Determine the bursting strength, in the standard atmosphere for testing textiles, as directed in [Test Method D3786](#) or [Test Method D3787](#).

*NOTE 2*—There is no overall correlation between the results obtained with the CRT machine equipped with a bursting attachment and the diaphragm bursting tester. Consequently, these two bursting testers cannot be used interchangeably. In case of controversy, the CRT machine equipped with a bursting attachment method shall prevail.

*NOTE 3*—The precision of the ball burst method using the CRT machine equipped with a bursting attachment and the precision of the diaphragm bursting tester method are being established by Subcommittee D13.59. The methods are accordingly not recommended for acceptance testing unless preceded by an interlaboratory check test in the laboratory of the purchaser and the laboratory of the seller using randomized replicate specimens of the material to be evaluated.

##### 7.2 Dimensional Change:

7.2.1 *Pressing and Finishing During Manufacturing*<sup>6</sup>—Mark specimen(s) as directed in AATCC TM135. Press and finish specimen(s) as agreed upon between the purchaser and the seller with respect to time cycles, temperature, steam, vacuum, and mechanical pressure of the press head. Measure the specimen(s) and calculate the dimensional change as directed in AATCC TM135.

7.2.1.1 If no agreement has been made between the purchaser and the seller, press the specimen(s) using a flat-bed steam press according to [Test Method D2724](#).

7.2.2 *Laundering*—Determine the maximum dimensional change after five launderings as directed in the applicable procedure in AATCC Method 135-1978 or as agreed upon between the buyer and the seller ([Note 4](#) and [Note 5](#)).

TABLE 1 Specification Requirements

*NOTE 1*—Grade for colorfastness and SA rating is based on a numerical scale of 5 for negligible or no color change, color transfer, or wrinkle to 1 for very severe color change, color transfer, or wrinkle. The numerical rating in [Table 1](#) or a higher numerical rating is acceptable.

Characteristic	Requirements	Section
Bursting strength (load) (ball burst)	50 lbf (222 N)	7.1
Dimensional change:		
Pressing and finishing	2 % max	7.2.1
After five launderings	5 % max	7.2.2
After three dry cleanings	3 % max	7.2.3
Growth	3 % max	7.2.4
Colorfastness:		
Burnt gas fumes, 2 cycles:		7.3.1
Shade change, original fabric	Grade 4 <sup>A</sup> min	
Shade change after one laundering or one dry cleaning	Grade 4 <sup>A</sup> min	
Sodium Hypochlorite Bleach	Grade 4 <sup>A</sup> min	7.3.7
Powdered Non-Chlorine Bleach	Grade 4 <sup>A</sup> min	7.3.8
Laundering: <sup>E</sup>		7.3.2
Shade change	Grade 4 <sup>A</sup> min	
Staining	Grade 3 <sup>B</sup> min	
Drycleaning:		7.3.3
Shade change	Grade 4 <sup>A</sup> min	
Crocking: <sup>E</sup>		7.3.4
Dry	Grade 4 <sup>C</sup> min	
Wet	Grade 3 <sup>C</sup> min	
Perspiration: <sup>E</sup>		7.3.5
Shade change	Grade 4 <sup>A</sup> min	
Staining	Grade 3 <sup>B</sup> min	
Light (40 AFUs) (xenon-arc)	Grade 4 <sup>A</sup> min	7.3.6
Fabric appearance (see <a href="#">7.4.1.1</a> )	SA 3.5 <sup>D</sup> min	7.4
Flammability	Class 1 or Class 2	7.5

<sup>A</sup> AATCC Gray Scale for Color Change.

<sup>B</sup> AATCC Gray Scale for Staining.

<sup>C</sup> AATCC 9-Step Chromatic Transference Scale.

<sup>D</sup> For durable press fabrics only.

<sup>E</sup> See [Note 7](#).

<sup>6</sup> The development of a standard method has been referred to Subcommittee D13.59 on Fabric Test Methods, General.

7.2.2.1 The wash conditions and drying procedure shall be as specified by the seller.

7.2.3 *Dry-cleaning*—Determine the maximum dimensional change after three dry cleanings in accordance with Section 10.1.1 through 10.1.5 of Test Methods **D2724** (Note 4 and Note 5).

7.2.4 *Growth*—Determine the growth of the fabric as directed in Test Methods **D2594**.

NOTE 4—Launderable fabrics are expected to be dry-cleanable except where all or part of the fabric is not dry-cleanable and is so labeled. For example, the fabric could contain a functional finish soluble in the solvent, or the fiber could be degraded by the solvent, which would be the case with poly(vinyl chloride) fiber. Goods labeled “Dry-cleanable” are to be dry-cleaned only.

NOTE 5—Specimens prepared for 7.2.1 may be used for 7.2.2 and 7.2.3 as desired. When this is done the dimensional change due to laundering or drycleaning is calculated using Eq 1. The dimensional change to pressing and finishing is determined on the fabric as it will reach the user. It is not additive to the dimensional change to laundering or drycleaning of the fabric as it will reach the consumer (see 6.1).

$$\text{Percent Dimensional Change} = 100(D_1 - D_2)/D_2 \quad (1)$$

where:

$D_1$  = measurement after laundering or dry-cleaning, and  
 $D_2$  = measurement after pressing and finishing.

### 7.3 Colorfastness:

7.3.1 *Burnt Gas Fumes*—Determine the colorfastness to burnt gas fumes on the original fabric and after one laundering or one dry cleaning as directed in AATCC TM23.

NOTE 6—Washing conditions shall be the same as those used in 7.2.2.1. Dry-cleaning conditions shall be the same as those used in 7.2.3.

7.3.2 *Laundering*—Determine the colorfastness to laundering as directed in the applicable procedure of AATCC TM61. The test conditions shall be as specified by the seller (Note 4).

NOTE 7—It has been reported that the results for staining, obtained by standard AATCC Test Methods, on fabrics dyed to dark shades that contain a combination of polyester and spandex, or their blends, may not show the full staining propensity of such fabrics in consumer use. It is, therefore, recommended that the staining results obtained by these tests not be used for acceptance testing of such fabrics.

7.3.3 *Dry cleaning*—Determine colorfastness to dry cleaning as directed in AATCC TM132 (Note 4).

7.3.4 *Crocking*—Determine colorfastness to dry and wet crocking as directed in AATCC TM8 for solid shades and AATCC TM116 for prints or as agreed upon between the purchaser and the seller (see Note 7).

7.3.5 *Perspiration*—Determine colorfastness to perspiration as directed in AATCC TM15 (see Note 7).

7.3.6 *Light*—Determine colorfastness to light as directed in AATCC TM16.3.

NOTE 8—There are distinct differences in spectral distribution between the various types of machines listed in AATCC TM16, with no overall correlations between them. Consequently, these machines cannot be used interchangeably. In case of controversy, results obtained with the Water-Cooled Xenon-Arc machine listed in Option 3 shall prevail.

7.3.7 *Colorfastness to Sodium Hypochlorite Bleach*—Determine colorfastness to sodium hypochlorite bleach as directed in AATCC TM188.

7.3.8 *Colorfastness to Powdered Non-Chlorine Bleach*—Determine colorfastness to non-chlorine bleach as directed in AATCC TM172.

7.4 *Fabric Appearance*—Determine the fabric appearance as directed in AATCC TM124 after laundering using the wash-and-wear cycle or the normal cycle as agreed upon between the purchaser and the seller, as specified in 7.2.2.1 for washable fabrics or as specified in 7.2.3 for dry-cleanable fabrics (see Note 4).

7.4.1 For fabrics not intended for use in durable-press garments, determine the fabric smoothness after pressing as specified in AATCC TM96.

7.4.1.1 The fabric smoothness durable-press (SA) rating of such fabrics, and the SA rating of dry-cleaned fabrics, shall have decreased no more than ½ SA rating from that of the fabric before it is laundered or dry-cleaned.

7.5 *Flammability*—The flammability requirements shall be as agreed upon between the purchaser and the seller, except when regulated by applicable Government mandatory standard (see section 2.3).

## 8. Keywords

8.1 necktie

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/*